

PRODUCT DESCRIPTION: FlexSet combines polymers with a specially-treated aggregate to create a rapid-setting, easy-to-apply, long-lasting and durable concrete repair. Repairs can be done in minutes, using only 4 simple steps. Originally developed for the military as a rapid runway repair material, FlexSet is an inexpensive alternative to traditional concrete restoration procedures. This innovative, patent-pending process provides a modern solution for an age-old problem. FlexSet repairs are guaranteed to perform.

Table 1. TX DMS-6170 Type I Physical Requirements

Test	Age at test	Method	Requirement	Result
Gel time, min.	-	Tex-614-J	5 to 60 min.	9 min.
Wet bond strength, psi	7 days	Tex-618-J	> 100 psi	176
Compressive strength, psi	24 hrs.	ASTM C579, B	> 200 psi	1,710 psi
	7 days		-	1,820 psi
	28 days		-	2,140 psi
Compressive stress at 0.1 in.	7 days	Tex-618-J	> 200 psi	733 psi
Resilience, %	7 days	Tex-618-J	> 90 %	97.2%*
				82.0%
Thermal compatibility	7 days	ASTM C884	No delam. or cracking after 9 cycles	Pass

* from earlier batch of material

Physical/Chemical Characteristics

Boiling Point:	428° F, 536° F	Specific Gravity: (H₂O)=1)	1.084, 0.942-.948
Vapor Pressure (mm Hg.):	NE	Melting Point:	N/A
Vapor Density: (AIR=1)	9.9	Evaporation Rate: (Butyl Acetate=1)	NE
Solubility in Water:	Insoluble, reacts with water to form carbon dioxide gas.		
Appearance and Odor:	Pale amber, odorless liquid		
Reactivity:	Stable, under normal, recommended storage conditions.		
Conditions to avoid:	Open flame and storage temperatures above 120°F.		

PACKAGING: Roklin Flexset is available in a 5 gallon kit which made up of equal volume "A" and "B" polymer, 30 pounds of a 2-12 and 60 mesh blend of treated aggregates and a 12 pound bag of treated 2-12 topping sand. The entire contents come in a 5 gallon bucket which the material is mixed in with a 1/2 HP drill. Shelf life is 12 months in unopened containers stored indoors. Bulk distribution is also available with the Roklin Strong Arm Polymer and Aggregate dispensing system.

Table 1. CT 551 Results

Material Property Tested	Age at test	Result
Compressive strength (MPa)	1 hr.*	4.25
	3 hr.*	7.00
	6 hr.*	7.45
	24 hr.	11.80
	7 day	12.55
Flexural strength (MPa)	24 hr.	5.10
	28 day	6.95
Bond strength (MPa)	24 hr.	1.40
	28 day	2.45
Modulus (MPa)	24 hr.	84.6
	28 day	163.0
Specific gravity	-	1.84
Absorption	-	0.33%

* stress at 10 mm displacement

A **FlexSet** concrete repair kit includes coated sand, bottles of "A" and "B" liquids, and a high-traction topping. **FlexSet** is mixed in its own bucket using an electric hand drill and a mixer. It reacts quickly after mixing, yet remains workable (with a lute, squeegee or trowel) for several minutes prior to thickening and setting. Repairs are completed in minutes and cure quickly with no shrinkage.

FlexSet is virtually unaffected by the environment, with durability surpassing other repairs. It is waterproof, non-flammable, and unaffected by gasoline, diesel, motor oils, jet fuel, anti-freeze or de-icing fluids.

FlexSet is also safe. The liquid polymers are odorless and non-flammable, with no fumes, no caustics, no acids, no solvents, no oxidizers, no flammables, no dust, and no heating. However, protective eyewear and gloves are required to prevent skin contact and avoid sensitization to the liquid polymer.

DIRECTIONS: Flexset can be applied in 4 simple steps:-

CLEAN SURFACE Apply to stable, clean, uncoated, dry surfaces.

PREPARE FLEXSET Mix polymers and sand, using a simple pail mixer and heavy-duty drill.

APPLY FLEXSET Pour and trowel FlexSet over deteriorated concrete.

ADD TOPPING SAND and after Flexset sets up open to traffic.



SYSTEMS INCORPORATED

20541 Pascal Way, Lake Forest, CA 92630

Tel: 1-877-FLEXSET 949-707-6111 Fax 949-707-6113

email Roklin@sbcglobal.net www.roklinsystemsinc.com